

Low Alloy Steels

1½Cr-½Mo CREEP RESISTING STEEL

DATA SHEET

A-12

METRODE PRODUCTS LTD
HANWORTH LANE, CHERTSEY
SURREY, KT16 9LL

Tel: +44(0)1932 566721
Fax: +44(0)1932 565168 Sales
Fax: +44(0)1932 569449 Technical
Fax: +44(0)1932 566199 Export
Email: info@metrode.com
Internet: http://www.metrode.com

Alloy type

1½Cr-½Mo alloyed steel consumables for elevated temperature service.

Materials to be welded

ASTM	BS EN & DIN
A387 Gr 11 & 12	13CrMo 4-5 (1.7355)
A182 F11 & F12	13CrMo 4-4 (1.7335)
A217 WC6 & WC11	16CrMo 4-4 (1.7337)
A234 WP11 & WP12	11CrMo 5-5 (1.7339)
A199 T11	GS-25CrMo 4 (1.7128)
A200 T11	GS-17CrMo 5-5 (1.7357)
A213 T11 & T12	
A335 P11 & P12	
BS	
	1501 Gr 620 & 621
	1502 Gr 620
	1503 Gr 620 & 621
	1504 Gr 621
	3100 Gr B2
	3604 Gr 620/440 & 621
	3059 Gr 620/460

Applications

These consumables are designed for prolonged elevated temperature service up to 550°C. Main areas of application are associated with **steam generating power plant**, eg **piping, turbine castings, steam chests, valve bodies and boiler superheaters**. Some of the consumables will also find service in refineries where they are used for **corrosion resistance** to sulphur bearing crude oil at 250-450°C. Some of the consumables will also find applications in the chemical and petro-chemical industries where they are used for **resistance to hydrogen attack** in the fabrication of **hydrocrackers, coal liquefaction plant** and **NH₃ pressure vessels** operating at up to 450°C. In the as-welded condition the consumables also provide a useful source of 300HV hardness weld deposit for build-up or

hardsurfacing to resist metal-to-metal wear and heavy impact.

Microstructure

After PWHT, the microstructure consists of tempered bainite.

Welding guidelines

Preheat and interpass temperature 200°C minimum, up to 300°C for thick sections. Maintain throughout welding cycle and some time after completion of welding.

PWHT

Apart from some special applications, PWHT will always be required. PWHT temperature is typically 690°C with time being dependent on section thickness.

Additional information

There are Technical Profiles available which cover some of the consumables on this data sheet. Additional information is available on Chromet 1X and Cormet 1.

Products available

Process	Product	Specification
MMA	Chromet 1	AWS E8018-B2
	Chromet 1L	AWS E7015-B2L
	Chromet 1X *	AWS E8018-B2
TIG/MIG	1CrMo	BS EN CrMo1Si
	ER80S-B2	AWS ER80S-B2
SAW	SA 1CrMo	AWS EB2
	LA436	BS EN SA AB 1
FCW	Cormet 1	AWS E81T1-B2

* Chromet 1X is the temper embrittlement resistant (TER) version of Chromet 1.

General Data for all 1½Cr-½Mo Electrodes

Description	Basic flux, metal powder type coatings on low carbon high purity core wire. Recovery is approximately 115% with respect to the core wire and 65% with respect to whole electrode. Moisture resistant coating gives very low metal hydrogen levels.						
Storage	<p>3 hermetically sealed ring-pull metal tins per carton, with unlimited shelf life. Direct use from tin will give hydrogen < 5ml/100g for longer than a working shift of 8h.</p> <p>For electrodes that have been exposed:</p> <p>Redry 250 – 300°C/1-2h to ensure H₂ < 10ml/100g, 300 – 350°C/1-2h to ensure H₂ < 5ml/100g. Maximum 420°C, 3 cycles, 10h total.</p> <p>Storage of redried electrodes at 50 – 200°C in holding oven or heated quiver: no limit, but maximum 6 weeks recommended. Recommended ambient storage conditions for opened tins (using plastic lid): < 60% RH, > 18°C.</p>						
Operating parameters	DC +ve or AC (OCV: 70V min)						
	Ø mm	2.5	3.2	4.0	5.0	6.0	
	min A	70	80	100	140	200	
	max A	110	140	180	240	300	
Fume data	Fume composition, wt % typical:						
	Fe	Mn	Cr	Ni	Cu	F	OES (mg/m ³)
	15	5	< 0.5	< 0.1	< 0.2	18	5

CHROMET 1

1½Cr-½Mo MMA electrode

Product description	MMA electrode meeting AWS and BS EN national standards suitable for most power generation applications.							
Specifications	AWS A5.5 E8018-B2 BS EN ISO 3580-A E CrMo1 B 3 2 BS EN ISO 3580-B E 5516-1CM BS 2493 (1CrMo B H) DIN 8575 ECrMo 1 B 2 6							
ASME IX Qualification	QW432 F-No 4, QW442 A-No 3							
Composition (weld metal wt %)	C	Mn*	Si	S	P	Cr	Mo	Cu
	min	0.05	0.50	--	--	1.00	0.45	--
	max	0.10	0.90	0.80	0.025	0.025	1.40	0.65
	typ	0.07	0.8	0.40	0.012	0.015	1.25	0.55
	* Mn may exceed AWS 0.90% max.							
All-weld mechanical properties	PWHT 690°C/1h			min	typical			
	Tensile strength			MPa	550	650		
	0.2% Proof stress			MPa	460	570		
	Elongation on 4d			%	19	25		
	Elongation on 5d			%	20	21		
	Reduction of area			%	--	70		
	Impact energy			+ 20°C	J	47	160	
				-10°C	J	--	100	
	Hardness			(AW)	HV	--	250	
				(PWHT)	HV	--	210	
	Preheat 150 – 250°C (BS EN), 200 – 300°C (BS), 160 – 190°C (AWS), 200 – 350°C (DIN).							
Packaging data	Ø mm	2.5	3.2	4.0	5.0	6.0		
	length mm	350	380	450	450	450		
	kg/carton	12.6	15.0	16.8	17.4	17.4		
	pieces/carton	627	372	243	159	111		

CHROMET 1L

Low carbon 1½Cr-½Mo MMA electrode

Product description	MMA electrode – 1½Cr-½Mo deposit with low carbon which produces lower hardness and residual stresses for resistance to sulphide stress corrosion cracking when operating in wet 'sour' environments. Also suitable for thin section joints which are to be left in the as-welded condition.																																																									
Specifications	AWS A5.5 E7015-B2L BS EN ISO 3580-A E CrMo1L B 3 2 BS EN ISO 3580-B E 5216-1CML BS 2493 (1CrMo L B H) DIN 8575 ECrMo 1 B 2 6																																																									
ASME IX Qualification	QW432 F-No 4, QW442 A-No 3																																																									
Composition (weld metal wt %)	<table border="1"> <thead> <tr> <th></th> <th>C</th> <th>Mn*</th> <th>Si</th> <th>S</th> <th>P</th> <th>Cr</th> <th>Mo</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>min</td> <td>0.03</td> <td>0.50</td> <td>--</td> <td>--</td> <td>--</td> <td>1.00</td> <td>0.45</td> <td>--</td> </tr> <tr> <td>max</td> <td>0.05</td> <td>0.90</td> <td>0.80</td> <td>0.025</td> <td>0.025</td> <td>1.40</td> <td>0.65</td> <td>0.15</td> </tr> <tr> <td>typ</td> <td>0.04</td> <td>0.8</td> <td>0.40</td> <td>0.012</td> <td>0.015</td> <td>1.25</td> <td>0.55</td> <td><0.10</td> </tr> </tbody> </table> <p>* Mn may exceed AWS 0.90% max.</p>									C	Mn*	Si	S	P	Cr	Mo	Cu	min	0.03	0.50	--	--	--	1.00	0.45	--	max	0.05	0.90	0.80	0.025	0.025	1.40	0.65	0.15	typ	0.04	0.8	0.40	0.012	0.015	1.25	0.55	<0.10														
	C	Mn*	Si	S	P	Cr	Mo	Cu																																																		
min	0.03	0.50	--	--	--	1.00	0.45	--																																																		
max	0.05	0.90	0.80	0.025	0.025	1.40	0.65	0.15																																																		
typ	0.04	0.8	0.40	0.012	0.015	1.25	0.55	<0.10																																																		
All-weld mechanical properties	<table border="1"> <thead> <tr> <th></th> <th colspan="2">PWHT 690°C/1h</th> <th>min</th> <th>typical</th> </tr> </thead> <tbody> <tr> <td>Tensile strength</td> <td colspan="2">MPa</td> <td>520</td> <td>600</td> </tr> <tr> <td>0.2% Proof stress</td> <td colspan="2">MPa</td> <td>390</td> <td>500</td> </tr> <tr> <td>Elongation on 4d</td> <td colspan="2">%</td> <td>19</td> <td>26</td> </tr> <tr> <td>Elongation on 5d</td> <td colspan="2">%</td> <td>20</td> <td>23</td> </tr> <tr> <td>Reduction of area</td> <td colspan="2">%</td> <td>--</td> <td>68</td> </tr> <tr> <td>Impact energy</td> <td>+ 20°C</td> <td>J</td> <td>--</td> <td>180</td> </tr> <tr> <td></td> <td>-10°C</td> <td>J</td> <td>--</td> <td>120</td> </tr> <tr> <td>Hardness</td> <td>(AW)</td> <td>HV</td> <td>--</td> <td>220</td> </tr> <tr> <td></td> <td>(PWHT)</td> <td>HV</td> <td>--</td> <td>200</td> </tr> </tbody> </table>									PWHT 690°C/1h		min	typical	Tensile strength	MPa		520	600	0.2% Proof stress	MPa		390	500	Elongation on 4d	%		19	26	Elongation on 5d	%		20	23	Reduction of area	%		--	68	Impact energy	+ 20°C	J	--	180		-10°C	J	--	120	Hardness	(AW)	HV	--	220		(PWHT)	HV	--	200
	PWHT 690°C/1h		min	typical																																																						
Tensile strength	MPa		520	600																																																						
0.2% Proof stress	MPa		390	500																																																						
Elongation on 4d	%		19	26																																																						
Elongation on 5d	%		20	23																																																						
Reduction of area	%		--	68																																																						
Impact energy	+ 20°C	J	--	180																																																						
	-10°C	J	--	120																																																						
Hardness	(AW)	HV	--	220																																																						
	(PWHT)	HV	--	200																																																						
Packaging data	<table border="1"> <tbody> <tr> <td>ø mm</td> <td>2.5</td> <td>3.2</td> <td>4.0</td> <td>5.0</td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>length mm</td> <td>350</td> <td>380</td> <td>450</td> <td>450</td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>kg/carton</td> <td>12.0</td> <td>14.1</td> <td>17.7</td> <td>18.0</td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>pieces/carton</td> <td>612</td> <td>414</td> <td>252</td> <td>168</td> <td></td> <td></td> <td></td> <td></td> </tr> </tbody> </table>								ø mm	2.5	3.2	4.0	5.0					length mm	350	380	450	450					kg/carton	12.0	14.1	17.7	18.0					pieces/carton	612	414	252	168																		
ø mm	2.5	3.2	4.0	5.0																																																						
length mm	350	380	450	450																																																						
kg/carton	12.0	14.1	17.7	18.0																																																						
pieces/carton	612	414	252	168																																																						

CHROMET 1X

1½Cr-½Mo alloyed MMA electrode for temper embrittlement resistance

Product description	MMA electrode – 1½Cr-½Mo deposit which meets specific requirements for improved temper embrittlement resistance with prolonged service at 400-600°C. Relevant trace elements (P, Sn, As, Sb) are controlled to ensure low Bruscato (X) and Watanabe (J) factors.																																																									
Specifications	AWS A5.5 E8018-B2 BS EN ISO 3580-A E CrMo1 B BS EN ISO 3580-B E 5516-1CM BS 2493 1CrMo B H DIN 8575 ECrMo 1 B 2 6																																																									
ASME IX Qualification	QW432 F-No 4, QW442 A-No 3																																																									
Composition (weld metal wt %)	<table border="1"> <thead> <tr> <th></th> <th>C</th> <th>Mn*</th> <th>Si*</th> <th>S</th> <th>P</th> <th>Cr</th> <th>Mo</th> <th>Cu</th> <th>Sn</th> <th>As</th> <th>Sb</th> </tr> </thead> <tbody> <tr> <td>min</td> <td>0.05</td> <td>0.50</td> <td>0.15</td> <td>--</td> <td>--</td> <td>1.00</td> <td>0.45</td> <td>--</td> <td>--</td> <td>--</td> <td>--</td> </tr> <tr> <td>max</td> <td>0.10</td> <td>0.90</td> <td>0.30</td> <td>0.015</td> <td>0.012</td> <td>1.40</td> <td>0.65</td> <td>0.15</td> <td>0.005</td> <td>0.010</td> <td>0.005</td> </tr> <tr> <td>typ</td> <td>0.06</td> <td>0.7</td> <td>0.25</td> <td>0.012</td> <td>0.009</td> <td>1.25</td> <td>0.55</td> <td><0.05</td> <td>0.002</td> <td>0.003</td> <td><0.002</td> </tr> </tbody> </table> <p>* Mn+Si < 1.10%</p> <p>Bruscato factor (X) : $\frac{10P + 5Sb + 4Sn + As}{100}$ (ppm) = 15 max</p> <p>Watanabe factor (J) : $(Mn+Si)(P + Sn) \times 10^4$ = 180 max</p>											C	Mn*	Si*	S	P	Cr	Mo	Cu	Sn	As	Sb	min	0.05	0.50	0.15	--	--	1.00	0.45	--	--	--	--	max	0.10	0.90	0.30	0.015	0.012	1.40	0.65	0.15	0.005	0.010	0.005	typ	0.06	0.7	0.25	0.012	0.009	1.25	0.55	<0.05	0.002	0.003	<0.002
	C	Mn*	Si*	S	P	Cr	Mo	Cu	Sn	As	Sb																																															
min	0.05	0.50	0.15	--	--	1.00	0.45	--	--	--	--																																															
max	0.10	0.90	0.30	0.015	0.012	1.40	0.65	0.15	0.005	0.010	0.005																																															
typ	0.06	0.7	0.25	0.012	0.009	1.25	0.55	<0.05	0.002	0.003	<0.002																																															

CHROMET 1X (continued)

All-weld mechanical properties	PWHT 690°C/1h ⁽¹⁾ (SC = step cooled)		min	typical	690°C/5h typical	690°C/5h + SC typical
	Tensile strength	MPa	550	610	610	595
	0.2% Proof stress	MPa	460	525	515	490
	Elongation on 4d	%	19	25	29	29
	Elongation on 5d	%	20	21	25	25
	Reduction of area	%	--	70	70	70
	Impact energy	+ 20°C J	47 ⁽²⁾	160	200	200
		- 30°C J	--	100	160	140
	Hardness	(AW) HV	--	300-320	--	--
		(PWHT) HV	--	200-210	220	190

(1) BS & AWS PWHT 690°C/1h, DIN 690°C/>30min, BS EN 720°C/1h.
(2) DIN & BS EN minimum average.

Packaging data	ø mm	2.5	3.2	4.0	5.0
	length mm	350	380	450	450
	kg/carton	12.6	15.0	16.8	17.4
	pieces/carton	627	372	243	159

1CrMo

Solid welding wire for TIG & MIG.

Product description	Copper coated wire for TIG and MIG welding of 1½Cr-½Mo steels, conforming to European specifications.																																															
Specifications	AWS A5.28 ER80S-G BS EN ISO 21952-A CrMo1Si (W = TIG, G = MIG) BS 2901: Pt1 (A32) DIN 8575 (SG CrMo 1)																																															
ASME IX Qualification	QW432 F-No 6, QW442 A-No 3																																															
Composition (wire wt %)	<table border="1"> <thead> <tr> <th></th> <th>C</th> <th>Mn</th> <th>Si</th> <th>S</th> <th>P</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>min</td> <td>0.08</td> <td>0.80</td> <td>0.50</td> <td>--</td> <td>--</td> <td>0.90</td> <td>--</td> <td>0.45</td> <td>--</td> </tr> <tr> <td>max</td> <td>0.14</td> <td>1.20</td> <td>0.80</td> <td>0.020</td> <td>0.020</td> <td>1.30</td> <td>--</td> <td>0.65</td> <td>0.4</td> </tr> <tr> <td>typ</td> <td>0.1</td> <td>1</td> <td>0.6</td> <td>0.010</td> <td>0.015</td> <td>1.2</td> <td><0.1</td> <td>0.5</td> <td>0.1</td> </tr> </tbody> </table>									C	Mn	Si	S	P	Cr	Ni	Mo	Cu	min	0.08	0.80	0.50	--	--	0.90	--	0.45	--	max	0.14	1.20	0.80	0.020	0.020	1.30	--	0.65	0.4	typ	0.1	1	0.6	0.010	0.015	1.2	<0.1	0.5	0.1
	C	Mn	Si	S	P	Cr	Ni	Mo	Cu																																							
min	0.08	0.80	0.50	--	--	0.90	--	0.45	--																																							
max	0.14	1.20	0.80	0.020	0.020	1.30	--	0.65	0.4																																							
typ	0.1	1	0.6	0.010	0.015	1.2	<0.1	0.5	0.1																																							
All-weld mechanical properties	PWHT 690°C/4h (AWS=1h)			min	typical		MIG																																									
	Tensile strength MPa 0.2% Proof stress MPa Elongation on 4d % Impact energy -10°C J Hardness HV(HB)			550 470 19 -- --	635 520 25 > 200 220(215)		590 480 26 > 115 195(190)																																									
Typical operating parameters	<table border="1"> <thead> <tr> <th></th> <th>TIG</th> <th>MIG</th> </tr> </thead> <tbody> <tr> <td>Shielding</td> <td>Argon</td> <td>Ar-5%CO₂</td> </tr> <tr> <td>Current</td> <td>DC-</td> <td>DC+</td> </tr> <tr> <td>Diameter</td> <td>2.4mm</td> <td>1.2mm</td> </tr> <tr> <td>Parameters</td> <td>100A, 12V</td> <td>280A, 26V</td> </tr> </tbody> </table>									TIG	MIG	Shielding	Argon	Ar-5%CO ₂	Current	DC-	DC+	Diameter	2.4mm	1.2mm	Parameters	100A, 12V	280A, 26V																									
	TIG	MIG																																														
Shielding	Argon	Ar-5%CO ₂																																														
Current	DC-	DC+																																														
Diameter	2.4mm	1.2mm																																														
Parameters	100A, 12V	280A, 26V																																														
Packaging data	ø mm	TIG		MIG																																												
	0.8	--		15kg reel																																												
	1.2	--		15kg reel																																												
	1.6	5kg tube		--																																												
	2.4	5kg tube		--																																												
	3.2	5kg tube		--																																												
Fume data	MIG fume composition (wt %) (TIG fume negligible)																																															
	Fe	Mn	Cr ³	Ni	Mo	Cu	OES (mg/m ³)																																									
	55	5	0.4	< 0.1	< 0.5	1.2	5																																									

ER80S-B2

Solid welding wire for TIG & MIG.

Product description	Copper coated wire for TIG and MIG welding 1¼Cr-½Mo creep resisting steels, conforming to the AWS/ASME specification.																																																	
Specifications	AWS A5.28 ER80S-B2 BS EN ISO 21952-B 1CM BS 2901: Pt1 (A32) DIN 8575 --																																																	
ASME IX Qualification	QW432 F-No 6, QW442 A-No 3																																																	
Composition (wire wt %)	<table border="1"> <thead> <tr> <th></th><th>C</th><th>Mn</th><th>Si</th><th>S</th><th>P</th><th>Cr</th><th>Ni</th><th>Mo</th><th>Cu</th></tr> </thead> <tbody> <tr> <td>min</td><td>0.07</td><td>0.40</td><td>0.40</td><td>--</td><td>--</td><td>1.20</td><td>--</td><td>0.40</td><td>--</td></tr> <tr> <td>max</td><td>0.12</td><td>0.70</td><td>0.70</td><td>0.020</td><td>0.020</td><td>1.50</td><td>0.20</td><td>0.65</td><td>0.35</td></tr> <tr> <td>typ</td><td>0.1</td><td>0.5</td><td>0.5</td><td>0.010</td><td>0.015</td><td>1.3</td><td><0.1</td><td>0.5</td><td>0.1</td></tr> </tbody> </table>											C	Mn	Si	S	P	Cr	Ni	Mo	Cu	min	0.07	0.40	0.40	--	--	1.20	--	0.40	--	max	0.12	0.70	0.70	0.020	0.020	1.50	0.20	0.65	0.35	typ	0.1	0.5	0.5	0.010	0.015	1.3	<0.1	0.5	0.1
	C	Mn	Si	S	P	Cr	Ni	Mo	Cu																																									
min	0.07	0.40	0.40	--	--	1.20	--	0.40	--																																									
max	0.12	0.70	0.70	0.020	0.020	1.50	0.20	0.65	0.35																																									
typ	0.1	0.5	0.5	0.010	0.015	1.3	<0.1	0.5	0.1																																									
All-weld mechanical properties	PWHT 690°C/4h (AWS=1h)				min	typical																																												
	Tensile strength				MPa	550	TIG	590																																										
	0.2% Proof stress				MPa	470	TIG	480																																										
Typical operating parameters	Elongation on 4d				%	19	TIG	26																																										
	Hardness				HV(HB)	--	TIG	195(190)																																										
	Impact energy				- 10°C	J	TIG	> 200																																										
Packaging data	Ø mm		TIG			MIG																																												
	0.8		--			15kg reel																																												
	0.9		--			15kg reel																																												
Fume data	MIG fume composition (wt %) (TIG fume negligible)																																																	
	<table border="1"> <thead> <tr> <th>Fe</th><th>Mn</th><th>Cr³</th><th>Ni</th><th>Mo</th><th>Cu</th></tr> </thead> <tbody> <tr> <td>55</td><td>5</td><td>0.4</td><td><0.1</td><td><0.5</td><td>1.2</td></tr> </tbody> </table>						Fe				Mn	Cr ³	Ni	Mo	Cu	55	5	0.4	<0.1	<0.5	1.2	OES (mg/m ³)																												
Fe	Mn	Cr ³	Ni	Mo	Cu																																													
55	5	0.4	<0.1	<0.5	1.2																																													
						5																																												

SA1CrMo

Solid welding wire for SAW.

Product description	Solid wire for Sub Arc Welding of 1½Cr-½Mo steels.								
Specifications	AWS A5.23 EB2 BS EN ISO 24598-A SCrMo1								
ASME IX Qualification	QW432 F-No 6, QW442 A-No 3								
Composition (typical)		C	Mn	Si	S	P	Cr		
	SA1CrMo wire	0.10	0.8	0.15	0.010	0.012	1.3		
Deposit with LA436		0.08	1.1	0.4	<0.01	<0.02	0.55		
All-weld mechanical properties (LA436 flux)	PWHT 690°C/1h			min	typical				
	Tensile strength			MPa	550	620			
	0.2% Proof stress			MPa	470	535			
	Elongation on 4d			%	20	25			
	Elongation on 5d			%	20	23			
Impact energy		+20°C		J	47	>47			
Typical operating parameters	Current: DC or AC; DC+ve is preferred For 2.4mm: 300-500A, 28-36V, 350-700mm/min travel								
Packaging data	Ø mm	SAW							
	2.4	25kg coil							
Fume data	SAW fume negligible								

LA436

Sub-arc flux

Product description	LA436 is agglomerated aluminate basic flux (Boniszewski BI ~1.6) with silicon pick-up of ~0.3% and manganese pick-up of ~0.4%.								
Specifications	AWS A5.23 F8 P0-EB2 B2 BS EN 760 SA AB 1 67 AC H5								
ASME IX Qualification	QW432 F-No --, QW442 A-No --								
Composition (typical)		C	Mn	Si	S	P	Cr		
	SA 1CrMo wire	0.10	0.8	0.15	0.010	0.012	1.3		
Deposit with LA436		0.08	1.1	0.4	<0.01	<0.02	0.55		
All-weld mechanical properties with SA 1CrMo wire				Typical PWHT 690-720°C/1-2h					
	Tensile strength			MPa	620				
	0.2% Proof stress			MPa	535				
	Elongation on 4d			%	25				
	Impact energy			+20°C	J	>47			
Typical operating parameters	Current: DC or AC; DC+ve is preferred 2.4mm: 300-500A, 28-36V, 350-700mm/min travel speed								
Packaging data	Metrode LA436 flux is supplied in sealed moisture resistant 25kg metal drums. Preferred storage conditions for opened drums: <60% RH, >18°C. If the flux has become damp or has been stored for a long period, it should be redried in the range 300-350°C/1-2h.								

CORMET 1

All-positional flux cored wire

Product description	Cormet 1 is an all-positional flux cored wire suitable for welding fixed pipework. Made using a high purity steel sheath with a metal recovery of about 90% with respect to the wire.									
Specifications	AWS A5.29 E81T1-B2C/M BS EN ISO 17634-B T55T1-1C/M-1CM									
ASME IX Qualification	QW432 F-No 6, QW442 A-No 3									
Composition (weld metal wt %)	C	Mn	Si	S	P	Cr	Mo	Cu		
	min	0.05	--	--	--	1.00	0.40	--		
	max	0.12	1.25	0.80	0.030	0.030	1.50	0.65		
All-weld mechanical properties	typ	0.06	1.0	0.3	0.01	0.01	1.3	0.55		
	PWHT 690°C/1-2h				min	typical				
	Tensile strength			MPa	550	650				
	0.2% Proof stress			MPa	470	550				
	Elongation on 4d			%	19	24				
	Elongation on 4d			%	17	22				
Operating parameters	Impact energy + 20°C			J	--	> 40				
	Hardness			HV	--	220				
Packaging data	Shielding gas: 80% Ar-20% CO ₂ at 20-25l/min. Proprietary gases may be used but argon should not exceed 80%. The wire is also suitable for use with 100% CO ₂ . (Note: for 100% CO ₂ shielding gas, voltage should be 1-2V higher.) Current: DC+ve ranges as below:									
	Ø mm	amp-volt range			typical	stickout				
	1.2	160 – 260A, 24-30V			190A, 25V	15 – 25mm				
	1.6	220 – 350A, 26-32V			260A, 28V	15 – 25mm				
Fume data	Fume composition (wt %)									
	Fe	Mn	Ni	Cr ³	Cr ⁶	Cu	F	OES (mg/m ³)		
	20	8	< 0.5	1	< 1	< 1	8	5		