

High Temperature Alloys

DATA SHEET

C-20

METRODE PRODUCTS LTD
 HANWORTH LANE, CHERTSEY
 SURREY, KT16 9LL
 Tel: +44(0)1932 566721
 Fax: +44(0)1932 565168 Sales
 Fax: +44(0)1932 569449 Technical
 Fax: +44(0)1932 566199 Export
 Email: info@metrode.com
 Internet: http://www.metrode.com

OXIDATION RESISTANT 253MA ALLOY

Alloy type

Iron based 22%Cr-10%Ni alloy with controlled additions of C, Si, N and rare earths (RE), predominantly cerium, with excellent oxidation resistance.

Materials to be welded

wrought

ASTM/UNS	S30815.
BS EN 10095	1.4818 X6CrNiSiNCe 19-10 1.4828 X15CrNiSi 20-12 1.4835 (X9CrNiSiNCe 21-11-2).
DIN	1.4893 (X8CrNiSiN 21 11). 1.4891 (X4CrNiSiN 18 10)).
Proprietary	Avesta 253MA

Also suitable for similar material:

ASTM UNS S30415
 Avesta 153MA

Applications

Designed to match equivalent alloys with good hot strength coupled with excellent resistance to oxidation up to about 1100°C. Resistance to sulphidation under oxidising conditions is superior to many higher nickel heat-resistant alloys. Resistance to nitriding and carburisation is satisfactory except under reducing conditions where higher nickel alloys are superior.

Also satisfactory for **dissimilar** combinations of materials with related levels of alloying. However, control of hot cracking in this high silicon weld metal is

dependent on some ferrite being present during solidification. Caution is therefore required when considering dilution by dissimilar materials which could promote fully austenitic solidification, such as type 310 and other high nickel alloys. Combinations with alloys stabilised with Ti and especially Nb should be avoided, due to the possibility of embrittlement by Si-rich eutectics with these elements.

Applications include **furnaces** and **furnace parts**, high temperature **flues**, **exhaust** and **heat recuperator systems**, combustion nozzles.

Microstructure

Austenite with controlled ferrite of about 5FN.

Welding guidelines

No preheat required, it is desirable to keep interpass below 150°C.

Related alloy groups


There are other consumables that also provide excellent oxidation resistance but they are generally more highly alloyed than the 253MA alloy.

Products available

Process	Product	Specification
MMA	Supermet 253MA	--

SUPERMET 253MA

Rutile electrode for matching alloy 253MA

Product description	<p>All-positional MMA electrode with an acid rutile flux system on alloyed core wire. Controlled Si and rare earth (RE) additions (mainly cerium) provide excellent oxidation resistance.</p> <p>Recovery is about 115% with respect to core wire, 65% with respect to whole electrode.</p>												
Specifications	There are no applicable national standards.												
ASME IX Qualification	QW432 F-No --, QW442 A-No --												
Composition (weld metal wt %)		C	Mn	Si	S	P	Cr	Ni	Mo	N	Cu	Ce *	FN
	min	0.04	--	1.4	--	--	21.0	9.0	--	0.14	--	--	3
	max	0.10	1.0	2.0	0.020	0.035	23.0	11.0	0.50	0.20	0.50	trace	10
	typ	0.06	0.8	1.5	0.01	0.02	22	10.3	0.1	0.16	0.1	0.005	5
* Cerium is present but actual value not reported on test certificate.													
All-weld mechanical properties	As welded						typical						
	Tensile strength					MPa	705						
	0.2% Proof stress					MPa	550						
	Elongation on 4d					%	40						
	Elongation on 5d					%	38						
	Reduction of area					%	50						
Operating parameters	DC +ve or AC (OCV: 50V min)												
													
	ø mm	2.5		3.2		4.0							
	min A	50		75		100							
	max A	75		120		155							
Packaging data	ø mm	2.5		3.2		4.0							
	length mm	300		350		350							
	kg/carton	11.4		13.5		14.4							
	pieces/carton	594		366		261							
Storage	<p>3 hermetically sealed ring-pull metal tins per carton, with unlimited shelf life. Direct use from tin is satisfactory for longer than a working shift of 8h. Excessive exposure of electrodes to humid conditions will cause some moisture pick-up and increase the risk of porosity.</p> <p>For electrodes that have been exposed: Redry 200 – 300°C/1-2h to restore to as-packed condition. Maximum 400° C, 3 cycles, 10h total. Storage of redried electrodes at 50 – 200°C in holding oven or heated quiver: no limit, but maximum 6 weeks recommended. Recommended ambient storage conditions for opened tins (using plastic lid): < 60% RH, > 18°C.</p>												
Fume data	Fume composition, wt % typical:												
		Fe	Mn	Ni	Cr	Cu	F	OES (mg/m ³)					
		9	6	1	7	<0.2	17	0.7					